

METZ 27

FLEXIBLE, HIGH STRENGTH CERAMIC TILE ADHESIVE



DESCRIPTION:

Metz 27 is a two part synthetic rubber latex cementitious adhesive, which greatly exceeds the requirements of Australian Standard AS 4992.1 for a C2TES2 adhesive. Metz 27 is a highly deformable, improved cementitious adhesive with slip resistance and extended open time. Metz 27 can be used to bond a wide range of ceramic tile to various backgrounds, including concrete, sand/cement screed, fibre cement and other tiles.

FEATURES AND BENEFITS:

- Exceeds requirements of AS 4992.1 for a C2TES2 adhesive.
- Exceeds requirements of AS 3958.1 for C2S1 adhesive for use in swimming pools.
- High bond strength to a wide range of materials.
- Can be used to bond highly vitrified or porcelain tiles.
- Highly flexible. Can take up substrate movements caused by expansion, vibration, thermal stress or other factors.
- Non-slump. Can be used to fix large format tiles to vertical surfaces.

RECOMMENDED:

As a thin bed tile adhesive for:

- Ceramic tiles, including highly vitrified and porcelain tiles to the following substrates:
 - Concrete
 - Sand/Cement screeds and renders
 - Fibre Cement Sheet
 - Many other surfaces (refer Metz for details)

Can be used in continuously immersed situations such as swimming pools.

NOT RECOMMENDED:

- For bed thicknesses above 6mm.
- For areas subjected to strong chemicals

PHYSICAL PROPERTIES: (Typical Values)

Density g/cm³: 1.55 - 1.65

Following properties tested in accordance with AS4992.2

Characteristic	Requirement*	Result
Tensile adhesion strength	≥ 1.0 N/mm ²	3.64 N/mm ²
Tensile adhesion strength after water immersion	≥ 1.0 N/mm ²	2.71 N/mm ²
Tensile adhesion strength after heat aging	≥ 1.0 N/mm ²	3.02 N/mm ²
Adhesion strength after freeze-thaw cycle	≥ 1.0 N/mm ²	3.17 N/mm ²
Open time: tensile adhesion test	≥ 1.0 N/mm ²	2.64 N/mm ²
Special Characteristic		
Slip (T)	≤ 0.5mm	0.41mm
Extended open time (E) after 30 minutes	≥ 0.5 N/mm ²	2.53 N/mm ²
Transverse deformation (S) for S2 adhesive	≥ 5mm	9.47mm
Standard Colour:	Off white	

* Requirement for C2 "Improved Adhesive"

COVERAGE: Theoretical quantities (allow for wastage)

1 x 20kg bag powder mixed with 8kgs liquid will cover 8.5m² with a 6x6mm notched trowel

1 x 20kg bag powder mixed with 8kgs liquid will cover 5.5m² with a 10x10mm notched trowel

APPLICATION TEMPERATURE:

The recommended temperature range for application is 10°C to 35°C.

At temperatures below 10°C, curing may be inhibited and final technical properties may be altered. At temperatures above 35°C, pot life and open time will be affected.



Acid Proofing & Industrial Flooring • Specialty Ceramic Tiles



METZ 27

FLEXIBLE, HIGH STRENGTH CERAMIC TILE ADHESIVE



INSTRUCTIONS FOR USE

1. Temperature of Working Area

Maintain a temperature of between 10°C and 35°C on Metz 27 liquid and powder, tiles, substrate and air during mixing, application and cure. At temperatures below 10°C Metz 27 may not cure fully. At temperatures above 35°C, initial set will take place too rapidly and open time will be greatly reduced. This difficulty can be overcome by mixing in a cooler area, cooling components and mixing equipment.

2. Surface Preparation

All surfaces must be clean and dry. Remove all oil, grease and other contaminants that may inhibit bond. Concrete surfaces must be free from laitance, form oils and curing compounds and be at least 14 days old.

3. Mixing

a) Equipment

Mechanical mixing is recommended. A low speed mixer should be used. High speed mixers can break down components in the material and cause air entrapment.

b) Mixing Proportions

	By Weight	By Volume
Metz 27 Liquid	1	1
Metz 27 Powder	2.5	1.7

The mixing proportions may be adjusted slightly to suit requirements.

c) Mixing Procedure

Place liquid in mixing container. Add powder gradually with constant stirring. Mix for at least 3 minutes until a smooth, lump free paste is obtained.

Note: Ensure you have the latest mixing instructions, refer www.metz.net.au for current data sheet version.

d) Pot Life

3-4 hours at 20°C.

e) Open time (time after application of adhesive during which tiles can be laid). At least 30 minutes at 23°C and 50% relative humidity. Note that this time will decrease with increase in temperature, decrease in humidity or increase in airflow.

Note: Increase in temperature will reduce both pot life and open time. Every 10°C will approximately halve both times.

4. Application

Spread only sufficient adhesive to cover an area that can be tiled within the open time of the product (30 minutes at 23°C). Do not lay tiles over adhesive that has skinned.

For mosaic and flat back tiles having dimensions less than 200x200mm. Use 6x6mm notched trowel

For larger tile sizes the following notched trowel sizes are recommended:

200x200 mm - 8 mm notched trowel

250x250 mm - 10 mm notched trowel

300x300 mm - 12 mm notched trowel

400x400 mm and above - 12 mm notched trowel

plus buttering of the tile.

Keyed back tiles:

Fill keys with adhesive prior to laying. In all cases, ensure the back of the tile is completely covered. Clean off excess adhesive with water before it begins to set.

5. Setting/Curing Time

Setting time: Overnight at 20°C

Full cure: 7 days at 20°C

6. Storage

Protect Metz 27 liquid from frost and low temperatures. Store powder in a cool, dry place. Protect bags from moisture. Under these conditions, minimum shelf life is 6 months.

7. Safety Precautions

Avoid contact with skin and eyes. Wear gloves and safety glasses. Avoid breathing dust. Wear dust mask when mixing.

For full safety precautions, refer to the Material Safety Data Sheet for each component.

- The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
- If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - Metz shall not be liable for any loss of damage including consequential loss or damage or loss of profits arising thereby;
 - Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.

REV 08/10

METZ SPECIALTY MATERIALS PTY LTD

A.C.N. 140 636 639

12 Turbo Road, Kings Park, NSW 2148

Facsimile: (02) 9671 4292 Phone: (02) 9671 1311

6 University Place, Clayton North, VIC 3168

Facsimile: (03) 9561 6944 Phone: (03) 9561 6144

Unit 16, 42 Smith Street, Capalaba QLD 4157

Facsimile: (07) 3823 5552 Phone: (07) 3823 5555

Distributor